

SUNVISION

Technical sheet

DICKSON®

| CHARACTERISTICS | VALUES | | UNITS | STANDARDS |
|-----------------|--------|------|-------|-----------|
| | WARP | WEFT | | |

GENERAL CHARACTERISTICS

| | | | | |
|----------------|------------------------------------------------------------------------|--|------------------|------------|
| Composition | High tenacity polyester PVC coated and solution dyed acrylic | | | |
| Finish | Cleangard special dirt-resistance and awning water resistant treatment | | | |
| Weave | Canvas | | | ISO 7211-1 |
| Weight | 275 | | g/m ² | ISO 3801 |
| Thickness | 0.74 | | mm | ISO 5084 |
| Openess factor | 12 | | % | EN 14500 |
| Width | 125 250 | | cm | EN 1773 |
| Roll length | 50 50 | | ml | |

FABRIC RESISTANCE

| | | | | |
|-----------------------|-----|-----|----------|-------------|
| Tensile strength | 80 | 80 | daN/5cm | ISO 13934-1 |
| Elongation at break | 23 | 23 | % | ISO 13934-1 |
| Tear strength | 5 | 5 | daN | ISO 13937-1 |
| Stiffness | 550 | 350 | mN | ISO 2493 |
| Elongation under load | 8 | 10 | % | MO LAB 025 |
| Resistance durability | 4 | | class /4 | EN 13561 |

COLOUR-FASTNESS

| | | | | |
|--------------------------------------|-----|--|----------|-------------|
| Colour fastness UV - outdoor - 1000h | 4-5 | | class /5 | ISO 105 B04 |
| Colour fastness UV - indoor | 7-8 | | class /8 | ISO 105 B02 |
| Colourfastness | 4 | | class /4 | EN 13561 |

USES

| | | | | |
|--------------------|-------------------------------------------------------------------------------------------------------------------------|--|-------|--|
| Temperature of use | -30 >> +70 | | C° | |
| Guarantee | 5 | | years | |
| Recommended use | Drop arm awning, Exterior velum, Pergola, Sail shade, Interior blind, Separation panel, Roll up valance, Screen pergola | | | |

This product's values may vary with a tolerance of ± 5%

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

FINISHING
CLEANGARD®
OUTDOOR TREATMENT
by DICKSON®

SUNACRYL®
OUTDOOR FIBRE
by DICKSON®



SUNVISION

Ficha técnica

DICKSON®

| CARACTERÍSTICAS | VALORES | | UNIDADES | NORMAS |
|-----------------|----------|-------|----------|--------|
| | URDIMBRE | TRAMA | | |

CARACTERÍSTICAS GENERALES

| | | | |
|---------------------|-----------------------------------------------------------------------------------|--|---------------------------|
| Composición | Hilo poliéster de alta tenacidad recubierto de PVC y hilo acrílico teñido en masa | | |
| Acabado | Tratamiento Cleangard especial toldo, antimanchas e impermeabilizante | | |
| Con armazón | lona | | ISO 7211-1 |
| Peso | 275 | | g/m ² ISO 3801 |
| Espesor | 0.74 | | mm ISO 5084 |
| Índice de apertura | 12 | | % EN 14500 |
| Anchos | 125 250 | | cm EN 1773 |
| Longitudes de corte | 50 50 | | ml |

RESISTENCIA DEL TEJIDO

| | | | | |
|---------------------------------|-----|-----|----------|-------------|
| Resistencia a la rotura | 80 | 80 | daN/5cm | ISO 13934-1 |
| Alargamiento a la rotura | 23 | 23 | % | ISO 13934-1 |
| Resistencia al desgarro | 5 | 5 | daN | ISO 13937-1 |
| Rigidez | 550 | 350 | mN | ISO 2493 |
| Deformación bajo carga | 8 | 10 | % | MO LAB 025 |
| Durabilidad de las resistencias | 4 | | class /4 | EN 13561 |

SOLIDEZ DE LOS COLORES

| | | | | |
|---------------------------------------|-----|--|----------|-------------|
| Solidez colores UV - exterior - 1000h | 4-5 | | class /5 | ISO 105 B04 |
| Solidez colores UV - interior | 7-8 | | class /8 | ISO 105 B02 |
| Durabilidad de los colores | 4 | | class /4 | EN 13561 |

USOS RECOMENDADOS

| | | | | |
|--------------------|---------------------------------------------------------------------------------------------------------------------------------------------------|--|------|--|
| Temperatura de uso | -30 >> +70 | | C° | |
| Garantía | 5 | | años | |
| Uso recomendado | Punto recto, Velum de exterior, Pérgola, Tensados vela, Cortina vertical para interior, Panel de separación, Bambalina enrollable, Screen pergola | | | |

FINISHING
CLEANGARD®
OUTDOOR TREATMENT
by DICKSON®

SUNACRYL®
OUTDOOR FIBRE
by DICKSON®



GARANTÍA
5
AÑOS

RESISTENCIA
TEÑIDOS EN MASA
COLORES

MADE IN

FRANCE

Los valores de este producto pueden variar con una tolerancia ± 5%

Dickson-Constant - SARL con 12 640 000 € de capital social - 381 347 970 RCS Lille Métropole

Polígono Can Calderón Avenida Progreso, 11 - 08840 Viladecans (Barcelona) - España

Tél. : (+34) 93 635 42 00 - Fax : (+34) 93 635 42 01 - www.dickson-constant.com/es/ES